

Technical specification

Underlay: Thermalay

Top surface	Stitch bonded crepe paper
Bottom Surface	Flat sponge rubber
Nominal thickness	+/- 6.70mm
Nominal roll weight	+/- 31.0Kg
Weight per unit area	+/- 3087g/m ²
Roll length	+/- 7.3m
Roll width	+/- 1.37m
Work of compression after 1000 impacts BS4098	> 90J/m ²
Retention of work of compression BS4098	> 75%
Loss in thickness after static loading BS4939	< 5.00%
Loss in thickness after Dynamic loading BS4052	< 5.00%
Resistance to cracking BS5808 (A)	Pass
Thermal resistance BS4745 (TOG Rating)	0.8 TOG



Head Office

Wool Classics 19 Victoria Industrial Estate Victoria Road London W3 6UU

T: +44 (0) 20 8961 7721 (General)
+44 (0) 20 7349 0090 (Sales)

F: +44 (0) 20 7349 0035

sales@woolclassics.com
samples@woolclassics.com

www.woolclassics.com